

Glass Properties	Soda Lime
Strain Point (°C)	525
Annealing Point (°C)	530
Softening Point (°C)	720
Working Point (°C)	1040
Expansion Coefficient x 10⁻⁷ cm/cm/°C	91
Density (g/cc)	2.50
Refractive Index 589.3nm	1.514
Volume Resistivity Log (W-cm)	7.1 @ 250°C
Volume Resistivity Log (W-cm)	5.7 @ 350°C
Dielectric Constant (k) @ 25°C, 1MHz	7.2
Loss Factor tand (10⁻⁴)	70
Young's Modulus	73 x 10³ N/mm²
Working Point (°C)	1040



800-325-4796

www.accu-glass.com