

<b>Glass Properties</b>	<b>Borosilicate (Low Expansion)</b>
<b>Strain Point (°C)</b>	<b>510</b>
<b>Annealing Point (°C)</b>	<b>560</b>
<b>Softening Point (°C)</b>	<b>820</b>
<b>Working Point (°C)</b>	<b>1270</b>
<b>Expansion Coefficient x 10<sup>-7</sup> cm/cm/°C</b>	<b>33</b>
<b>Density (g/cc)</b>	<b>2.23</b>
<b>Refractive Index 589.3nm</b>	<b>1.473</b>
<b>Volume Resistivity Log (W-cm)</b>	<b>8.0 @ 250°C</b>
<b>Volume Resistivity Log (W-cm)</b>	<b>6.5 @ 350°C</b>
<b>Dielectric Constant (k) @ 25°C, 1MHz</b>	<b>4.6</b>
<b>Loss Factor %</b>	<b>37</b>
<b>Young's Modulus</b>	<b>63 x 10<sup>3</sup>N/mm<sup>2</sup></b>



800-325-4796

[www.accu-glass.com](http://www.accu-glass.com)