

<b>Glass Properties</b>	<b>Borosilicate (Medium Expansion )</b>
<b>Strain Point (°C)</b>	<b>530</b>
<b>Annealing Point (°C)</b>	<b>570</b>
<b>Softening Point (°C)</b>	<b>785</b>
<b>Working Point (°C)</b>	<b>1140</b>
<b>Expansion Coefficient x 10<sup>-7</sup> cm/cm/°C</b>	<b>55</b>
<b>Density (g/cc)</b>	<b>2.33</b>
<b>Refractive Index 589.3nm</b>	<b>1.49</b>
<b>Volume Resistivity Log (W-cm)</b>	<b>7.0 @ 250°C</b>
<b>Volume Resistivity Log (W-cm)</b>	<b>5.7 @ 350°C</b>
<b>Dielectric Constant (k) @ 25°C, 1MHz</b>	<b>5.8</b>
<b>Loss Factor %</b>	<b>0.84</b>
<b>Young's Modulus</b>	<b>10.4 x 10<sup>6</sup> psi</b>



800-325-4796

[www.accu-glass.com](http://www.accu-glass.com)