

<b>Glass Properties</b>	<b>Lead Free</b>
<b>Strain Point (°C)</b>	<b>455</b>
<b>Annealing Point (°C)</b>	<b>485</b>
<b>Softening Point (°C)</b>	<b>675</b>
<b>Working Point (°C)</b>	<b>1020</b>
<b>Expansion Coefficient x 10<sup>-7</sup> cm/cm/°C</b>	<b>92</b>
<b>Density (g/cc)</b>	<b>2.62</b>
<b>Refractive Index 589.3nm</b>	<b>1.523</b>
<b>Volume Resistivity Log (W-cm)</b>	<b>8.8 @ 250°C</b>
<b>Dielectric Constant (k) @ 25°C, 1MHz</b>	<b>6.0 @ 20°C</b>
<b>Loss Factor tand (10<sup>-4</sup>)</b>	<b>0.017</b>
<b>Young's Modulus</b>	<b>72.5 N/mm<sup>2</sup></b>



800-325-4796

[www.accu-glass.com](http://www.accu-glass.com)